

Zero field splitting parameter of Mn^{2+} doped guanidine zinc sulphate crystal -a theoretical study

Ram Kripal, Lal Chandra Shukla, Upendra Mani Tripathi

EPR Laboratory, Department of Physics, University of Allahabad, Allahabad-211002, India

E-mail: ram_kripal2001@rediffmail.com

Received: March 02, 2021; Accepted: March 19, 2021; Published: March 29, 2021

Cite this article: Kripal, R., Shukla, L. C., & Tripathi, U. M. (2021). Zero field splitting parameter of Mn^{2+} doped guanidine zinc sulphate crystal -a theoretical study. *Boson Journal of Modern Physics*, 8(1), 18-23. Retrieved from <http://www.scitecresearch.com/journals/index.php/bjomp/article/view/2032>.

Abstract.

A theoretical investigation of crystal field parameters (CFP) and zero-field splitting (ZFS) parameter D of Mn^{2+} doped guanidine zinc sulphate (GZS) crystals at room temperature (RT) is done with the help of superposition model and the perturbation theory. The ZFS parameter D determined here is in good agreement with the experimental value reported earlier. The conclusion of experimental study that Mn^{2+} substitutes for Zn^{2+} in GZS is supported by our theoretical investigation. The values of D without and with local distortion are $11174.3 \times 10^{-4} \text{ cm}^{-1}$ and $702.4 \times 10^{-4} \text{ cm}^{-1}$, respectively, while the experimental value is $702.0 \times 10^{-4} \text{ cm}^{-1}$.

Keywords: A. Organic compounds; A. Single crystal; D. Crystal fields; D. Optical properties; D. Electron paramagnetic resonance.

1. Introduction

Electron paramagnetic resonance (EPR) studies are useful for the knowledge of structural distortions and local site symmetry of transition ions in crystals [1-7]. EPR spectra of these ions are frequently analyzed with the help of microscopic spin-Hamiltonian (MSH) theory. Using this theory, the spin Hamiltonian (SH) parameters from EPR can be correlated with optical absorption and structural parameters. Both the experimental and theoretical studies indicate that the spin Hamiltonian parameters of transition ions (d^5 (6S)) in crystals are very sensitive to local distortion. Therefore, the SH theory is widely used in crystals.

The crystal-field (CF) parameters of d^5 ion are obtained using superposition model (SPM) [8, 9]. The zero field splitting (ZFS) parameters are determined using CF parameters [10]. Mn^{2+} ion is important as its ground state is $^6S_{5/2}$ [11-15]. The electron spin is affected by high order interaction of crystalline electric field and in external magnetic field the orientation of spins is free [16]. As S state ions have large spin-lattice relaxation time, Mn^{2+} ion gives well resolved EPR lines [15-19] at room temperature (RT).

In the present paper, the CF parameters are determined using SPM and these parameters with MSH theory give ZFS parameter for Mn^{2+} ion at the substitutional Zn^{2+} site in guanidine zinc sulphate (GZS) crystal at RT.

2. Crystal Structure

The crystal structure of GZS, $Zn[C(NH_2)_3]_2(SO_4)_2$ belongs to space group $I\bar{4}2d$ with unit cell dimensions $a = 0.9515 \text{ nm}$ and $c = 1.4351 \text{ nm}$, and there exist four molecules per unit cell ($Z = 4$) [20]. A network of zinc and sulphate ions constitutes the main feature of the structure. Four oxygen ions form a distorted tetrahedral environment around the Mn^{2+} ion, as shown in Fig. 1.




Fig. 1 Environment around Mn^{2+} ion.

3. Theoretical Investigation

The Mn^{2+} ion in GZS crystal substitutes at Zn^{2+} site [21]. The SH of $3d^5$ ion in crystal field of axial symmetry is given as [2, 22, 23]

$$\begin{aligned} \mathcal{H} = & g \mu_B B \cdot S + D \left\{ S_z^2 - \frac{1}{3} S(S+1) \right\} \\ & + \left(\frac{a}{6} \right) [S_x^4 + S_y^4 + S_z^4 - \frac{1}{5} S(S+1)(3S^2 + 3S - 1)] \\ & + \frac{F}{180} \{ 35S_z^4 - 30S(S+1)S_z^2 + 25S_z^2 - 6S(S+1) + 3S^2(S+1)^2 \} \\ & + A(I \cdot S) \end{aligned} \quad (1)$$

where the first term gives electronic Zeeman interaction, B is the external magnetic field, g is the spectroscopic splitting factor and μ_B is Bohr magneton. The second, third, and fourth terms represent the second order axial, fourth-rank cubic and fourth-rank axial ZFS terms [2]. The fifth term provides the hyperfine interaction term. S, D, a, F are the effective spin vector, second order axial, fourth-rank cubic and fourth-rank axial ZFS parameters, respectively. An isotropic approximation for the electronic Zeeman interaction is used in case of Mn^{2+} ions [2, 24, 25].

The Hamiltonian for a d^5 ion is given as

$$\mathcal{H} = \mathcal{H}_0 + \mathcal{H}_{cf} + \mathcal{H}_{so}$$

$$\text{where } \mathcal{H}_{cf} = \sum_{kq} B_{kq} C_q^k \quad (2)$$

gives the crystal field Hamiltonian. \mathcal{H}_0 and \mathcal{H}_{so} represent free ion Hamiltonian and spin-orbit (SO) coupling, respectively. Since the spin-spin coupling is very small [26-28], its contribution has been neglected in Eq. (2). The crystal field of SO interaction is considered as perturbation term [29,30]. The strong-field scheme calculation for F-state ions was given by Macfarlane [31]. The SO contribution to the ZFS parameter D for $3d^5$ ions in axial symmetry is given by [30]

$$D^{(4)}(SO) = \left(\frac{\xi^2}{63P^2G} \right) [14B_{44}^2 - 5B_{40}^2] - \left(\frac{3\xi^2}{70P^2D} \right) B_{20} [B_{20} - 14\xi] \quad (3)$$

where $P = 7(B+C)$, $G = 10B+5C$ and $D = 17B+5C$. P , G , and D represent the energy separations between the excited quartets and the ground sextet. Racah parameters B and C give the electron-electron repulsion. Only fourth order term is taken in Eq. (3) as other perturbation terms are negligible [32]. The parameters B , C and ξ , in terms of the average covalency parameter N , are given as, $B = N^4 B_0$, $C = N^4 C_0$ and $\xi = N^2 \xi_0$, where B_0 and C_0 are the Racah parameters and ξ_0 , the spin-orbit coupling parameter, for free ion [33, 34]. $B_0 = 960 \text{ cm}^{-1}$, $C_0 = 3325 \text{ cm}^{-1}$, $\xi_0 = 336 \text{ cm}^{-1}$ [2] for Mn^{2+} ion are used here. N can be obtained with the help of equation

$$N = \left(\sqrt{B/B_0} + \sqrt{C/C_0} \right) / 2, \quad (4)$$

By using SPM the CF parameters for Mn^{2+} in GZS crystal are calculated and substituting these in Eq. (3) ZFS parameter D is obtained. Similar method has been used for finding ZFS parameters by many other workers [35].

To understand the crystal-field splitting, the SPM is effectively used. This model has also been applied for $3d^n$ ions [8, 32, 36]. The crystal field parameters, using this model, are found from the equations [37]

$$B_{20} = -2 \bar{A}_2 \left(\frac{R_0}{R_{10} + \Delta R_1} \right)^{t_2} - 4 \bar{A}_2 \left(\frac{R_0}{R_{20} + \Delta R_2} \right)^{t_2} \quad (5)$$

$$B_{40} = 16 \bar{A}_4 \left(\frac{R_0}{R_{10} + \Delta R_1} \right)^{t_4} + 12 \bar{A}_4 \left(\frac{R_0}{R_{20} + \Delta R_2} \right)^{t_4} \quad (6)$$

$$B_{44} = 2\sqrt{70} \bar{A}_4 \left(\frac{R_0}{R_{20} + \Delta R_2} \right)^{t_4} \quad (7)$$

in which R_0 is the reference distance, in general chosen as the average value of all four bond lengths (for axial symmetry).

4. Results and Discussion

The average value of two out of four Mn^{2+} -O bond lengths are given as $R_{10} = 0.20936 \text{ nm}$ and the average value of the rest two bond lengths are also given as $R_{20} = 0.20936 \text{ nm}$. ΔR_1 and ΔR_2 represent the distortion

parameters. \bar{A}_2 , \bar{A}_4 and t_k are the intrinsic parameter and power law exponent, respectively. In tetrahedral

coordination, $\overline{A_4}(R_0) = (-27/16)Dq$ [10]. For $3d^5$ ions, $\frac{\overline{A_2}}{\overline{A_4}}$ is in the range 8-12 [32, 36]. The power law exponent for Mn^{2+} ion is taken as $t_2 = 3$, $t_4 = 7$. Semi-ab initio calculations are performed for other transition metal ions to obtain the intrinsic parameter values in SPM,

The values of B , C and Dq are obtained (for oxygen ligands) [38] using optical study [39] as 917, 2254 and 756 cm^{-1} , respectively. First no local distortion is considered and the value of D is estimated. For this, taking $\frac{\overline{A_2}}{\overline{A_4}} = 8$ and $R_0 = 0.215 \text{ nm}$, the sum of ionic radii of $Mn^{2+} = 0.08 \text{ nm}$ and $O^{2-} = 0.135 \text{ nm}$, which is slightly larger than the average distance of four ligands; the B_{kq} parameters are obtained as: $B_{20} = -66319.5 \text{ cm}^{-1}$, $B_{40} = 43026.6 \text{ cm}^{-1}$, $B_{44} = 25713.3 \text{ cm}^{-1}$ and the value of D as: $D = 11174.3 \times 10^{-4} \text{ cm}^{-1}$. EPR study gives the experimental value of D as: $D = 702.0 \times 10^{-4} \text{ cm}^{-1}$ [40]. From above it is found that the theoretical value is larger than the experimental one.

Now, taking local distortions as $\Delta R_1 = 0.04794 \text{ nm}$ and $\Delta R_2 = 0.00002 \text{ nm}$, $R_0 = 0.215 \text{ nm}$ and ratio $\frac{\overline{A_2}}{\overline{A_4}} = 8$, the B_{kq} parameters are obtained as: $B_{20} = -56109.5 \text{ cm}^{-1}$, $B_{40} = 24233.6 \text{ cm}^{-1}$, $B_{44} = 25696.1 \text{ cm}^{-1}$ and the value of D as: $D = 702.4 \times 10^{-4} \text{ cm}^{-1}$, in reasonable agreement with the experimental one: $D = 702.0 \times 10^{-4} \text{ cm}^{-1}$.

5. Conclusions

Axial symmetry zero-field splitting parameter D for Mn^{2+} in GZS crystal has been determined using superposition model and perturbation theory. The theoretical D is in reasonable agreement with the experimental one when local distortion is taken into consideration. This theoretical investigation suggests that Mn^{2+} ion occupies substitutional Zn^{2+} site supporting the conclusion drawn from the experimental EPR study.

ACKNOWLEDGEMENT

The authors are thankful to the Head, Department of Physics, University of Allahabad for providing the facilities of the department.

References

- [1] C. Rudowicz, S. K. Misra, SPIN-HAMILTONIAN FORMALISMS IN ELECTRON MAGNETIC RESONANCE (EMR) AND RELATED SPECTROSCOPIES, *Appl. Spectrosc. Rev.* **36** (2001)11-63.
- [2] Z. Y. Yang, C. Rudowicz, Y. Y. Yeung, Microscopic spin-Hamiltonian parameters and crystal field energy levels for the low C_3 symmetry Ni^{2+} centre in $LiNbO_3$ crystals, *Physica B* **348** (2004) 151-159.
- [3] Z. Y. Yang, Y. Hao, C. Rudowicz, Y. Y. Yeung, Theoretical investigations of the microscopic spin Hamiltonian parameters including the spin-spin and spin-other-orbit interactions for $Ni^{2+}(3d^8)$ ions in trigonal crystal fields, *J. Phys.: Condens. Matter* **16** (2004) 3481-3494.
- [4] T. H. Yeom, Y. M. Chang, S. H. Choh, C. Rudowicz, Experimental and Theoretical Investigation of Spin-Hamiltonian Parameters for the Low Symmetry Fe^{3+} Centre in $LiNbO_3$, *Phys. Stat. Sol.* **b185** (1994) 409-415.
- [5] P. Gnutek, Z. Y. Yang, C. Rudowicz, Modeling local structure using crystal field and spin Hamiltonian parameters: the tetragonal $Fe_K^{3+}-O_I^{2-}$ defect center in $KTaO_3$ crystal, *J. Phys.: Condens. Matter* **21** (2009) 455402.
- [6] Y. Y. Yeung, D. J. Newman, Superposition-model analyses for the $Cr^{3+} 4A_2$ ground state, *Phys. Rev.* **B34** (1986) 2258-2265.
- [7] D. J. Newman, D. C. Pryce, W. A. Runciman, Superposition model analysis of the near infrared spectrum of Fe (super 2+) in pyrope-almandine garnets, *Am. Mineral.* **63** (1978) 1278-1281;
- [8] A. Edgar, Electron paramagnetic resonance studies of divalent cobalt ions in some chloride salts, *J. Phys.* **C 9** (1976) 4304; G. Y. Shen, M. G. Zhao, Analysis of the spectrum of Fe^{2+} in -pyrope

- garnets, *Phys. Rev.* **B30** (1984) 3691- 3703,
- [9] S. K. Misra in: *Handbook of ESR (Vol.2)*, eds. C. P. Poole Jr., H. A. Farach, Springer, New York, 1999, Chapter IX, p. 291.
- [10] H. Anandlakshmi, K. Velavan, I. Sougandi, R. Venkatesan, P. S. Rao, Single crystal EPR studies of Mn(II) doped into zinc ammonium phosphate hexahydrate ($\text{ZnNH}_4\text{PO}_4 \cdot 6\text{H}_2\text{O}$): A case of interstitial site for bio-mineral analogue, *Pramana* **62** (2004) 77- 86.
- [11] P. S. Rao, Single crystal EPR study of Mn(II)-doped magnesium potassium Tutton's salt, *Spectrochim. Acta* **A 49** (1993) 897-901.
- [12] S. K. Misra, Estimation of the Mn^{2+} zero-field splitting parameter from a polycrystalline EPR spectrum, *Physica* **B203** (1994) 193-200.
- [13] B. R. Mc Garvey, *Electron Spin Resonance of Transition Metal Complexes*, in: *Transition Metal Chemistry*, Vol. 3, ed. R. L. Carlin, Marcel Dekker, New York, 1966.
- [14] S. Natarajan and J. K. Mohana Rao, The crystal structure of diglycine calcium chloride tetrahydrate, *Curr. Sci.* **45** (1976) 490-491.
- [15] A. Abragam, B. Bleaney, *Electron Paramagnetic Resonance of Transition Ions*, Clarendon Press, Oxford, 1970.
- [16] H. A. Kuska, M.T. Rogers, *Radical Ions*, E. T. Kaiser, L. Kevan, Eds., Interscience, New York, 1968.
- [17] V. S. X. Anthonisamy, M. Velayutham, R. Murugesan, Spin-lattice relaxation of Co(II) in hexaquoocobalt(II) picrylsulphonate tetrahydrate: An estimate from EPR line width of the dopant, Mn(II), *Physica* **B262** (1999) 13-19.
- [18] T. H. Yeom, S. H. Choh, M. L. Du, A theoretical investigation of the zero-field splitting parameters for an Mn^{2+} centre in a BiVO_4 single crystal, *J. Phys.: Condens. Matter* **5** (1993) 2017-2024.
- [19] M. J. D. Powell, J. R. Gabriel, D. F. Johnston, Ground-State Splitting for $d^5 \ ^6\text{S}$ Ions in a Cubic Field, *Phys. Rev. Lett.* **5**(1960)145-146.
- [20] H. Watanabe, On the Ground Level Splitting of Mn^{++} and Fe^{+++} in Nearly Cubic Crystalline Field, *Prog. Theor. Phys.***18** (1957) 405-420.
- [21] C. N. Morimoto, E. C. Lingafelter, The crystal structure of zinc guanidinium sulfate, *Acta Cryst.* **B26** (1970)335-341.
- [22] M. L. Du, M. G. Zhao, The eighth-order perturbation formula for the EPR cubic zero-field splitting parameter of $d^3(^6\text{S})$ ion and its applications to MgO : Mn^{2+} and $\text{MnCl}_2 \cdot 2\text{H}_2\text{O}$, *J. Phys. C: Solid State Phys.***18** (1985) 3241-3248.
- [23] W. L. Yu, Cubic zero-field splitting of a ^6S state ion, *Phys. Rev.* **B39** (1989) 622-632.
- [24] Z. Y. Yang, An investigation of the EPR zero-field splitting of Cr^{3+} ions at the tetragonal site and the Cd^{2+} vacancy in RbCdF_3 : Cr^{3+} crystals, *J. Phys.: Condens. Matter* **12** (2000) 4091-4096.
- [25] D. J. Newman, B. Ng, The superposition model of crystal fields, *Rep. Prog. Phys.* **52** (1989) 699-763.
- [26] W. L. Yu, M. G. Zhao, Spin-Hamiltonian parameters of ^6S state ions, *Phys. Rev.* **B 37** (1988) 9254-9267.
- [27] K. D. Singh, S. C. Jain, T. D. Sakore, A. B. Biswas, The crystal and molecular structure of zinc lactate trihydrate, *Acta Cryst.* **B31** (1975) 990-993.
- [28] C. Rudowicz, H. W. F. Sung, Can the electron magnetic resonance (EMR) techniques measure the crystal (ligand) field parameters?, *Physica* **B300** (2001) 1-26.
- [29] C. J. Radnell, J. R. Pilbrow, S. Subramanian, M. T. Rogers, Electron paramagnetic resonance of Fe^{3+} ions in $(\text{NH}_4)_2\text{SbF}_5$, *J. Chem. Phys.* **62** (1975) 4948-4952.
- [30] J. A. Weil, J. R. Bolton, *Electron Paramagnetic Resonance: Elementary Theory and Practical Applications*, second ed., Wiley, New York, 2007.
- [31] W. L. Yu, M. G. Zhao, Determination of the crystalline structure of Mn^{2+} : CaZnF_4 by EPR and optical spectra of Mn^{2+} , *J. Phys. C: Solid State Phys.* **17**(1984) L525-L527.
- [32] J. F. Clare, S. D. Devine, Application of the superposition model to non-S-state ions, *J. Phys.* **C17**(1984) L581-L584.
- [33] R. M. Macfarlane, Zero Field Splittings of t_2^3 Cubic Terms, *J. Chem. Phys.* **47** (1967) 2066-2073; Perturbation Methods in the Calculation of Zeeman Interactions and Magnetic Dipole Line Strengths for d^3 Trigonal-Crystal Spectra, *Phys. Rev.* **B1** (1970) 989-1004.
- [34] M. H. L. Pryce, Spin-Spin Interaction within Paramagnetic Ions, *Phys. Rev.* **80** (1950) 1107-1108.
- [35] R. R. Sharma, T. P. Das, R. Orbach, Zero-Field Splitting of S-State Ions. I. Point-Multipole Model, *Phys. Rev.* **149** (1966) 257-269.
- [36] W. L. Yu, M. G. Zhao, Zero-field splitting and the d-d transitions of Mn^{2+} on Ca(II) sites in $\text{Ca}_5(\text{PO}_4)_3\text{F}$, *Phys. Stat. Sol.* **b140** (1987) 203-212.
- [37] Y. Y. Yeung, Superposition model and its applications, in: *Optical Properties of 3d-Ions in Crystals*,

- Spectroscopy and Crystal Field Analysis (Chapter 3, pp.95-121), M. G. Brik and N. M. Avram (Eds.), Springer: Heidelberg, New York, Dordrecht, London, 2013.
- [38] Q. Wei, Investigations of the Optical and EPR Spectra for Cr^{3+} Ions in Diammonium Hexaaqua Magnesium Sulphate Single Crystal, *Acta Phys. Polon.* **A 118** (2010) 670-672.
- [39] R. Kripal, H. Govind, S. K. Gupta, M. Arora, EPR and optical absorption study of Mn^{2+} -doped zinc ammonium phosphate hexahydrate single crystals, *Physica* **B392** (2007) 92-98.
- [40] T. T. Hoa, N. D. The, S. McVitie, N. H. Nam, L. V. Vu, T. D. Canh, N. N. Long, Optical properties of Mn-doped ZnS semiconductor nanoclusters synthesized by a hydrothermal process, *Opt. Mat.* **33**(2011)308-314.
- [41] K. Gruszka, R. Hrabanski, J. Ozga, Z. Czapl, EPR study of guanidine zinc sulphate crystals, *Nukleonika* **58** (2013) 387-390.